



P.O. Box 4300 - 185 Concession St.  
 Lakefield - Ontario - KOL 2H0  
 Phone: 705-652-2000  
 FAX: 705-652-6365

On behalf of; AO  
 Attn :  
 Accrue Minerals Inc  
 Mr Andy Lee GGM

March 30, 2011

Date Rec. : 10 March 2011  
 LR Report : CA02525-MAR11

## CERTIFICATE OF ANALYSIS

### Final Report

Sample ID	H2O %	Si %	Al2O3 %	Mg %	CaO %	Na %	K %	Ti %	P %
1: Sample 1	4.42	2.31	6.37	1.29	1.52	< 0.01	< 0.01	0.08	0.01
3: Sample 2	4.49	2.34	6.48	1.31	1.41	< 0.01	< 0.01	0.08	0.01
5: Sample 3	4.59	2.30	6.33	1.26	1.63	< 0.01	< 0.01	0.08	0.01
7: Sample 4	2.77	2.66	3.30	2.13	0.25	< 0.01	< 0.01	0.01	< 0.01
9: Sample 5	2.15	2.28	2.48	1.62	0.24	< 0.01	< 0.01	0.02	< 0.01
11: Sample 6	3.51	2.30	3.20	1.93	0.49	< 0.01	< 0.01	0.03	< 0.01
<b>Ave:</b>	<b>3.65</b>	<b>2.36</b>	<b>4.70</b>						<b>&lt;0.01</b>

Sample ID	Mn %	Cr %	Co %	Ni %	Sn %	Zn %	S %	Fe %	Fe2+ as FeO %
1: Sample 1	0.31	1.88	0.09	1.19	< 0.01	0.03	0.02	50.14	0.27
3: Sample 2	0.33	1.86	0.09	1.19	< 0.01	0.03	0.02	50.47	0.28
5: Sample 3	0.33	1.86	0.09	1.17	< 0.01	0.03	0.02	50.28	0.30
7: Sample 4	0.68	1.75	0.18	1.54	0.01	0.04	< 0.01	55.36	0.50
9: Sample 5	0.67	1.79	0.25	1.39	< 0.01	0.04	< 0.01	57.28	0.64
11: Sample 6	0.66	3.53	0.21	1.31	< 0.01	0.05	< 0.01	54.50	0.44
<b>Ave:</b>				<b>1.30</b>			<b>0.015</b>	<b>53.00</b>	<b>0.40</b>

Party Quality Analysis - suitable for commercial exchange  
 Assay basis: Dried at 105 °C.



Project Coordinator



**\* 50,000 MT Stockpile - Sizing as follows:**

300-200 mm	4,5%	
200-150 mm	8,0%	
150-100 mm	12,5%	
100 - 50 mm	26,7%	[ Sizes: 150 – 10mm = +/- 84% of Total Ore Volume]
50 - 25 mm	34,0%	
25 - 10 mm	10,0%	
10- mm	4,3%	

**\* Note:**

**Sizing of Stockpile was not undertaken by SGS Staff – Sizing details above provided by Owners.**